

**GENERAL SPECIFICATION****COCKBURN BRICKIES GREY**

Values stated within this specification are based upon test results from grab samples. Individual results may from time to time lie outside these ranges and such occurrences should not necessarily be regarded as failure of the sampled batch to conform to this general specification.

Parameter	Method	Units	Typical	Range	AS1316 Limits
<b>Mortar</b>					
Water Retentivity	AS1316.4	%	80	75 – 85	70% min
Air Content	AS1316.5	%	21	18 - 24	10% min 25% max
<b>Setting Times</b>					
Initial	AS1316.2	mins	90	75 – 105	75 min min
Final	AS1316.2	mins	150	120 - 180	12 hr max
<b>*Compressive Strengths</b>					
7 Day	AS1316.6	MPa	27	24 – 30	3.5 MPa min
28 Day	AS1316.6	MPa	30	27 – 33	6 MPa min