

GENERAL SPECIFICATION**COCKBURN BRICKIES LITE**

Values stated within this specification are based upon test results from grab samples. Individual results may from time to time lie outside these ranges and such occurrences should not necessarily be regarded as failure of the sampled batch to conform to this general specification.

Parameter	Method	Units	Typical	Range	AS1316 Limits
Mortar					
Water Retentivity	AS1316.4	%	78	73 - 83	70% min
Air Content	AS1316.5	%	19	17 - 21	10% min 25% max
Setting Times					
Initial	AS1316.2	mins	105	75 - 135	75 min min
Final	AS1316.2	mins	180	135 - 225	12 hr max
*Compressive Strengths					
7 Day	AS1316.6	MPa	30	26 - 34	3.5 MPa min
28 Day	AS1316.6	MPa	32	28 - 36	6 MPa min