

**GENERAL SPECIFICATION****COCKBURN BRICKIES LITE COASTAL M4**

Values stated within this specification are based upon test results from grab samples. Individual results may from time to time lie outside these ranges and such occurrences should not necessarily be regarded as failure of the sampled batch to conform to this general specification.

Parameter	Method	Units	Typical	Range	AS1316 Limits
<b>Mortar</b>					
Water Retentivity	AS1316.4	%	76	70 - 82	70% min
Air Content	AS1316.5	%	17	14 - 20	10% min 25% max
<b>Setting Times</b>					
Initial	AS1316.2	mins	105	75 - 135	75 min min
Final	AS1316.2	mins	165	135 - 195	12 hr max
<b>*Compressive Strengths</b>					
7 Day	AS1316.6	MPa	34	31 - 37	3.5 MPa min
28 Day	AS1316.6	MPa	36	33 - 39	6 MPa min